

IN THE CLAIMS

129. (previously presented) A method of making mesoporous silica materials, comprising the steps of

- (a) combining a silica precursor with an aqueous solvent, an acid and a surfactant having an ammonium cation into a silica precursor solution,
- (b) templating the silica precursor with the surfactant and obtaining the mesoporous material from the templated silica precursor,
- (c) forming said silica precursor solution into a preform; and
- (d) rapidly evaporating said aqueous solvent from said preform for obtaining the mesoporous material, wherein the improvement comprises:
 - (e) providing said aqueous solvent in an amount resulting in complete hydrolysis and providing said acid in an amount maintaining a hydrolyzed precursor and avoiding gelation or precipitation; and
 - (f) providing said surfactant and said silica precursor in a mole ratio that is above a lower mole ratio that produces a non-porous silica phase and below an upper mole ratio that produces a lamellar phase.

130. (previously presented) The method as recited in claim 129, wherein said lower mole ratio is about 0.05.

131. (previously presented) The method as recited in claim 129, wherein said upper mole ratio is about 0.3.

132. (previously presented) The method as recited in claim 129, wherein said acid is added in an amount resulting in a pH of said silica precursor solution of from about 1 to about 4.

133. (previously presented) The method as recited in claim 132, wherein said pH is about 2.

134. (previously presented) The method as recited in claim 129, wherein the step of forming includes diluting with an alcohol.

135. (previously presented) The method as recited in claim 134, wherein said alcohol is ethanol.

136. (previously presented) The method as recited in claim 129, wherein said aqueous solvent, said acid, and said surfactant are premixed before combining with said silica precursor.

137. (previously presented) The method as recited in claim 129, wherein said mesoporous material is in a geometric form selected from the group consisting of fiber, powder, and film.

138. (previously presented) The method as recited in claim 129, wherein said forming is spin-casting.

139. (previously presented) The method as recited in claim 129, wherein said forming is spraying.

140. (previously presented) The method as recited in claim 129, further comprising adding a pre-polymer or a polymer to said silica precursor solution making a pituitous mixture.

141. (previously presented) The method as recited in claim 129, wherein said forming is drawing.

142. (previously presented) The method as recited in claim 129, wherein said forming is squeegeeing.

143. (previously presented) The method as recited in claim 129, further comprising the step of adding a metal compound to the silica precursor solution.

144. (previously presented) The method as recited in claim 143, wherein said metal compound is selected from the group consisting of metal halide, metal nitrate, and combinations thereof.

145. (previously presented) The method as recited in claim 144, wherein said metal halide is a metal chloride.

146. (previously presented) The method as recited in claim 144, wherein said metal is selected from the group of aluminum, iron and combinations thereof.

147. (previously presented) The method as recited in claim 129, wherein said silica precursor is an alkoxide silica precursor or a tetrachlorosilane.

148. (previously presented) The method as recited in claim 129, wherein said aqueous solvent amount is characterized by a ratio of said aqueous solvent to said silica precursor of about 7.

149. (previously presented) The method as recited in claim 129, wherein said acid amount is characterized by a ratio of said acid to said silica precursor of about 0.1.

150. (previously presented) The method as recited in claim 129, further comprising adding a swelling agent to the silica precursor solution.

151. (previously presented) The method as recited in claim 150, wherein said swelling agent is 1,3,5-trimethylbenzene.

152. (previously presented) The method as recited in claim 129, further comprising the step of calcining the mesoporous material.

153. (previously presented) A method of making a mesoporous silica film, comprising the steps of

(a) combining a silica precursor with an aqueous solvent, an acid and a surfactant having an ammonium cation into a silica precursor solution,

(b) templating the silica precursor with the surfactant and obtaining the mesoporous material from the templated silica precursor,

(c) forming said silica precursor into a preform; and

(d) rapidly evaporating said aqueous solvent from said preform for obtaining the mesoporous material, wherein the improvement comprises:

- (i) said silica precursor is tetraethoxysilane;
- (ii) providing said aqueous solvent in a superstoichiometric amount and providing said acid in an amount maintaining a hydrolyzed precursor and avoiding gelation or precipitation;
- (iii) providing said surfactant and said silica precursor in a mole ratio that is above a lower mole ratio that produces a non-porous silica phase and below an upper mole ratio that produces a lamellar phase; and
- (iv) said forming includes diluting with an alcohol.

154. (previously presented) The method as recited in claim 153, further comprising adding a pre-polymer or a polymer to said silica precursor solution making a pituitous mixture.

155. (previously presented) The method as recited in claim 153, wherein said rapidly evaporating is by spin-casting.

156. (previously presented) A method of making a mesoporous film on a substrate, the method comprising the steps of:

- (a) combining a silica precursor with an aqueous solvent, an acid catalyst and an ammonium cationic surfactant into a precursor solution;
- (b) dispensing said precursor solution onto the substrate;
- (c) forming a film by evaporation of the solvent in less than 5 minutes; and
- (d) heating the film on the substrate to a temperature sufficient to decompose the surfactant, thereby producing a mesoporous film on the substrate.

157. (previously presented) The method of claim 156 wherein the precursor solution is a silica precursor solution and wherein the surfactant and the silica precursor solution are in a mole ratio that is above a lower mole ratio that produces a non-mesoporous silica phase and below an upper mole ratio that produces a lamellar phase.

158. (previously presented) The process of claim 156, wherein the film exhibits an index of refraction between 1.16 and that of silica.

159. (previously presented) A process to form mesostructured films, comprising:

- (a) preparing a precursor sol containing a soluble source of silica, an aqueous solvent, an ammonium cationic surfactant and an acid catalyst; and
- (b) depositing the precursor sol on a substrate wherein evaporation of solvent and water in less than 5 minutes causes the formation of said mesostructured films on the substrate surface.

160. (previously presented) The process of claim 159 wherein the aqueous solvent and the catalyst are provided in amounts that maintain a hydrolyzed precursor sol while avoiding gelation or precipitation.

161. (previously presented) The process of claim 159 wherein the soluble source of silica is a silica precursor alkoxide or tetrachlorosilane and wherein the surfactant and the soluble source of silica are in a mole ratio that is above a lower mole ratio that produces a non-porous silica phase and below an upper mole ratio that produces a lamellar phase.

162. (previously presented) The process of claim 159, wherein the ammonium cationic surfactant further includes alkyl triethylammonium chloride or bromide surfactants with different chain lengths.

163. (previously presented) The process of claim 159, further comprising the step of calcining said film at 450°C.

164. (previously presented) The process of claim 159, wherein the precursor sol is deposited on a substrate by spin coating.

165. (previously presented) The process of claim 159, wherein said soluble source of silica is an alkoxide silica precursor or tetrachlorosilane.

166. (previously presented) The process of claim 159, wherein the films exhibit an index of refraction between 1.16 and that of silica.

167. (previously presented) A process to form a mesoporous structure, comprising:

- (a) preparing a precursor sol containing a soluble source of silica, an alcohol and water solvent, an ammonium cationic surfactant, and an acid catalyst, wherein said solvent is provided in an amount resulting in complete hydrolysis and said acid catalyst is in an amount to maintain a hydrolyzed precursor and to avoid gelation or precipitation in said precursor sol;
- (b) forming the precursor sol into a preform;
- (c) evaporating said solvent from the preform at a rate that forms a mesostructured material; and
- (d) calcining the mesostructured material to form a mesoporous structure.

168. (previously presented) The process of claim 167, wherein said precursor sol contains alcohol which is a byproduct of hydrolysis, and said mesoporous structure is a film.

169. (previously presented) The process of claim 167, wherein said preform is a droplet, said alcohol is a byproduct of hydrolysis, and said sol is spray dried to form a powder.

170. (previously presented) The process of claim 167, wherein said drying is preformed in less than 5 minutes.

171. (previously presented) The process of claim 167, wherein said precursor sol contains dilutant alcohol, and wherein the mesoporous structure is a film.

172. (previously presented) The process of claim 167, wherein the mesoporous structure is a film and wherein the film exhibits an index of refraction of between 1.16 and that of silica.

173. (previously presented) The process of claim 167, wherein the said precursor sol contains alcohol which is a byproduct of hydrolysis, and wherein said mesostructure is a film.

174. (previously presented) The process of claim 173, wherein the film exhibits an index of refraction of between 1.16 and that of silica.

175. (previously presented) The process of claim 167, wherein said preform is a droplet, wherein said alcohol is a byproduct of hydrolysis, and wherein said precursor sol is spray dried.

176. (previously presented) The process of claim 167, wherein said evaporating is performed in less than 5 minutes.

177. (previously presented) The process of claim 167, wherein said soluble source of silica includes a silica alkoxide precursor or tetrachlorosilane.

178. (previously presented) A process to form a mesoporous structure, comprising:

(a) preparing a precursor sol containing a soluble source of silica, an alcohol and water solvent, an ammonium cationic surfactant, and an acid catalyst, wherein said solvent is provided in an amount resulting in complete hydrolysis and said acid is in amount to maintain a hydrolyzed precursor and to avoid gelation or precipitation in said precursor sol;

(b) forming the precursor sol into a preform;

(c) evaporating said solvent from the preform at a rate that forms a mesostructured material, wherein said mesostructured material contains surfactant; and

(d) calcining the mesostructured material to form a mesoporous structure.

179. (previously presented) A process to form a mesostructure, comprising:

(a) preparing a precursor sol containing a soluble source of silica, water and alcohol solvent, an ammonium cationic surfactant and an acid catalyst; and

(b) evaporating said solvent in less than 5 minutes to cause the formation of a mesostructure, wherein said mesostructure contains surfactant.

180. (previously presented) The process of claim 179, wherein the mesostructure is a film, and wherein the film exhibits an index of refraction of between 1.16 and that of silica.

181. (previously presented) A process to form a mesostructure, comprising:
(a) preparing a precursor sol containing a soluble source of silica, a water and alcohol solvent, an ammonium cationic surfactant and an acid catalyst, and
(b) evaporating said solvent in less than 5 minutes to cause the formation of a mesostructure.

182. (previously presented) The process of claim 181, wherein said solvent is evaporated in less than 1 minute.

183. (previously presented) The process of claim 181, wherein said solvent is evaporated in less than 10 seconds.

184. (previously presented) The process of claim 183, wherein the mesostructure is a film, and wherein the film exhibits an index of refraction of between 1.16 and that of silica.

185. (previously presented) The process of claim 181, wherein the said precursor sol contains both dilutant alcohol and alcohol which is a byproduct of hydrolysis, and wherein said mesostructure is a film.

186. (previously presented) The process of claim 181, wherein said preform is a droplet, said alcohol is a byproduct of hydrolysis, and said sol is spray dried.

187. (previously presented) The process of claim 181, wherein the ammonium cationic surfactant further includes alkyl triethylammonium chloride or bromide surfactants with different chain lengths.

188. - 189. (canceled)